

Clareed.



● Items to be used

- Liquid A 50ml x1
- Liquid B 50ml x1
- Glass Resurfacing Polish 100ml x1
- Accelerator 17ml x3
- Dropper x2
- Blending bottle x1
- Black/white applicator sponge x1
- Yellow/black polishing sponge x1
- Micro suede cloth x1
- Dropper bottle for accelerator x1

1 Washing

Wash the windshield with car shampoo and then rinse it with plenty of water.

Wipe it off using a clean cloth.

2 Preparation

Blow off the remaining water using a blower so that the surface dries quickly.

Put masking tape on all weather stripping surrounding the windshield if necessary. Because it may become clouded when it comes in contact with Glass Resurfacing Polish.

3 Cleaning

Now we are removing oily residue on the glass surface using the included Glass Resurfacing Polish for a stronger bond of the Clareed to the surface.

Put the Glass Resurfacing Polish on the included blue sponge.

Polish the glass surface with an up and down motion, then with a side to side motion until the surface becomes clear and smooth.

Wipe it off using a slightly damp clean cloth, then wipe using a dry clean cloth.

Clareed.



4 Blending

Pour Liquid A into a blending bottle up to the scale mark #1.

Pour Liquid B up to the scale mark #2 as well.

Do not touch the top edge of the bottle with the dropper.

Because maybe there is Liquid A remaining on the top edge of the bottle.

If the dropper contacts with Liquid A and it is put back into Liquid B bottle, it will react.

Shake the bottle well.

5 Application of Accelerator

Cut the micro suede cloth into 8 pieces and fold in half. Use dropper bottle to instill the Accelerator on the cloth. Immediately apply the Accelerator to the glass surface thinly and evenly.

Apply the solution on 1/6-1/4 each part of the glass surface and wipe it like spreading with other cloth before it gets dried.

Wash the cloth before reuse.


Leave 10-20 minutes before applying the main liquid.

6 Application of Clareed coating agent

Apply a small amount of the blended Clareed on the included black sponge uniformly.

Apply it to the windshield with an up and down motion and side to side motion.

Do not leave empty spaces.



※Photo of applicator sponge for reference

7 Wipe to complete

Let the applied Clareed dry for about 10 minutes, then wipe with a clean cloth until the excess is removed using the same up and down motion and side to side motion gently and completely.

Take the masking tape off, and then you are done.